

C03300: FOOTINGS/ SLAB ON GRADE

PART 1 - GENERAL

- 1.1 SUMMARY
1. The Section specifies cast-in-place concrete, including formwork, reinforcement, concrete materials, mixture design, placement procedures, and finishes.
1.2 SUBMITTALS
A. Product Data: For each type of product indicated.
B. Design Mixtures: For each concrete mixture.
C. Shop Drawings: For steel reinforcement.
D. Material: Test reports & certificates.
1.3 QUALITY ASSURANCE
A. Manufacturer Qualifications: A firm experienced in manufacturing ready-mixed concrete products and that complies with ASTM C 94/C 94M requirements for production facilities and equipment.
1.4 CONCRETE MATERIALS
A. Cementitious Materials: Use the following cementitious materials, of the same type, brand, and source, throughout Project.
B. Portland Cement: ASTM C 150, Type I or II, unless otherwise noted.
C. Normal-Weight Aggregates: ASTM C 33, graded, 3/4-inch (19-mm) nominal maximum coarse-aggregate size.
D. Water: ASTM C 94/C 94M and potable.
E. Air-Entraining Admixture: ASTM C 250.
F. Chemical Admixtures: Provide admixtures certified by manufacturer to be compatible with other admixtures and that will not contribute water-soluble chloride ions exceeding those permitted in hardened concrete. Do not use calcium chloride or admixtures containing calcium chloride.
1.5 Retarding Admixtures: ASTM C 494/C 494M, Type B.
2. Plasticizing and Retarding Admixture: ASTM C 1017/C 1017M, Type II.
2.4 VAPOR RETARDERS
A. Plastic Vapor Barrier: 6 mil polyethylene film.
2.5 CURING MATERIALS
A. Absorbent Cover: ASHTO M 182, Class 2, burlap cloth made from jute or kenaf, weighing approximately 9 oz./sq. yd. (305 g/m2) when dry.
B. Moisture-Retaining Cover: ASTM C 171, polyethylene film or white burlap-polyethylene sheet.
C. Walker: Potable.
D. Clear, Waterborne, Membrane-Forming Curing and Sealing Compound: ASTM C 1315, Type 1, Class A
2.6 RELATED MATERIALS
A. Expansion- and Isolation-Joint-Filler Strips: ASTM D 1751, asphalt-saturated cellulose fiber.
2.7 CONCRETE MIXTURES
A. Prepare design mixtures for each type and strength of concrete, proportioned on the basis of laboratory trial mixture or field test data, or both, according to ACI 301.
B. Proportion normal-weight concrete mixture as follows:
1. Minimum Compressive Strength for footings and slab on grade: 3000 psi at 28 days; all other locations, use 4000 psi, unless noted otherwise.
2. Slump Limit: 1 inch (25 mm) - 4 inches (100 mm), @ (200 mm) if a plasticizer is used.
3. Air Content: 3 - 6 percent for all exterior concrete.
2.8 CONCRETE MIXING
A. Ready-Mixed Concrete: Measure, batch, mix, and deliver concrete according to ASTM C 94/C 94M and ASTM C 1116, and furnish batch ticket information.
1. When air temperature is between 65 and 90 deg F (19 and 32 deg C), reduce mixing and delivery time from 1-1/2 hours to 75 minutes; when air temperature is above 90 deg F (32 deg C), reduce mixing and delivery time to 90 minutes.
PART 3 - EXECUTION
3.1 FORMWORK
A. Design, erect, shore, brace, and maintain formwork according to ACI 301 to support vertical, lateral, static, and dynamic loads, and construction loads that might be applied, until sufficient concrete is cast and cured.
B. Construct formwork so concrete members and structures are of size, shape, alignment, elevation, and position indicated, within tolerance limits of ACI 117.
C. Chamfer exterior corners and edges of permanently exposed concrete.
3.2 EMBEDDED ITEMS
A. Place and secure anchorage devices and other embedded items required for adjoining work that is attached to or supported by cast-in-place concrete. Use setting drawings, templates, diagrams, instructions, and directions furnished with items to be embedded.
3.3 VAPOR RETARDERS
A. Plastic Vapor Retarders: Place, protect, and repair vapor retarders according to ASTM E 1043 and manufacturer's written instructions.
1. Lap joints 6 inches (150 mm) and seal with manufacturer's recommended tape.
3.4 STEEL REINFORCEMENT
A. General: Comply with CRSI's "Manual of Standard Practice" for placing reinforcement.
1. Do not cut or puncture vapor retarder. Repair damage and reset vapor retarder before placing concrete.
3.5 JOINTS
A. General: Construct joints true to line with faces perpendicular to surface plane of concrete.
B. Construction Joints: Install so strength and appearance of concrete are not impaired, at locations indicated or as approved by Architect.
C. Construction Joints in Slabs-on-Grade: Form weakened-plane contraction joints, sectioning concrete into areas as indicated. Construct contraction joints for a depth equal to at least one-fourth of concrete thickness as follows:
1. Grooved Joints: Form contraction joints after initial floating by grooving and finishing each edge of joint to a radius of 1/8 inch (3.2 mm). Repeat grooving of contraction joints after applying surface finishes. Eliminate groove tool marks on concrete surfaces.
2. Sawed Joints: Form contraction joints with power saws equipped with shatterproof abrasive or diamond-rimmed blades. Cut 1/8-inch (3.2 mm) wide joints into concrete when cutting action will not tear, abrade, or otherwise damage surface and before concrete develops random contraction cracks.
3. Isolation Joints in Slabs-on-Grade: After removing formwork, install joint-filler strips at slab junctions with vertical surfaces, such as column pedestals, foundation walls, grade beams, and other locations, as indicated.
3.6 CONCRETE PLACEMENT
A. Before placing concrete, verify that installation of formwork, reinforcement, and embedded items is complete and that required inspections have been performed.
B. Do not add water to concrete during delivery, at the project site or during placement unless approved by the architect or engineer.
C. Deposit concrete continuously in one layer or in horizontal layers of such thickness that no new concrete will be placed on concrete that has hardened enough to cause seams or planes of weakness. If a section cannot be placed continuously, provide construction joints as indicated. Deposit concrete to avoid segregation.
1. Consolidate placed concrete with mechanical vibrating equipment according to ACI 301.
D. Cold-Weather Placement: Comply with ACI 306.1.
E. Hot-Weather Placement: Comply with ACI 301.
3.7 FINISHING FORMED SURFACES
A. Rough-Formed Finish: As-cast concrete texture imparted by form-facing material with tie holes and defects repaired and patched. Remove fins and other projections that exceed specified limits on formed-surface irregularities.
1. Apply to concrete surfaces not exposed to public view.
B. Smooth-Formed Finish: As-cast concrete texture imparted by form-facing material, arranged in an orderly and symmetrical manner with a minimum of seams. Repair and patch tie holes and defects. Remove fins and other projections that exceed specified limits on formed-surface irregularities.
1. Apply to concrete surfaces exposed to public view.
C. Related Unformed Surfaces: At tops of walls, horizontal offsets, and similar unformed surfaces adjacent to formed surfaces, strike off smooth and finish with a texture matching adjacent formed surfaces. Continue final surface treatment of formed surfaces uniformly across adjacent unformed surfaces, unless otherwise indicated.
3.8 FINISHING FLOORS AND SLABS
A. General: Comply with ACI 302.1R recommendations for screeding, straightening, and finishing operations for concrete surfaces. Do not wet concrete surfaces.
B. Wood Float Finish: Areas scheduled to receive quarry or ceramic tile are to be finished to a slightly gritty surface texture with straight continuous strokes with a stiff bristle push broom, do not steel trowel any areas to receive tile. Broom Finish: Apply a broom finish to exterior concrete platforms, steps, and ramps, and elsewhere as indicated.
3.9 CONCRETE PROTECTING AND CURING
A. General: Protect freshly placed concrete from premature drying and excessive cold or hot temperatures. Comply with ACI 308.1 for cold-weather protection and ACI 301 for hot-weather protection during curing.
B. Evaporation Retarder: Apply evaporation retarder to unformed concrete surfaces if hot, dry, or windy conditions cause moisture loss approaching 0.2 lb/sq. ft. x h (1 kg/sq. m x h) before and during finishing operations. Apply according to manufacturer's written instructions after placing, screeding, and bull floating or troweling concrete, but before float finishing.
C. Cure concrete according to ACI 308.1, by one or a combination of the following methods:
1. Moisture Curing: Keep surfaces continuously moist for not less than seven days.
2. Moisture-Retaining-Cover Curing: Cover concrete surfaces with moisture-retaining cover for curing concrete, placed in widest practicable width, with sides and ends lapped at least 12 inches (300 mm), and sealed by waterproof tape or adhesive. Care for cover more than seven days. Immediately repair any holes or tears during curing period using cover material and waterproof tape.
3. Curing and Sealing Compound: Apply uniformly to floors and slabs indicated in a continuous operation by power spray or roller according to manufacturer's written instructions. Recoat areas subjected to heavy rainfall within three hours after initial application. Repeat process 24 hours later and apply a second coat. Maintain continuity of coating and repair damage during curing period.
3.10 CONCRETE SURFACE REPAIRS
A. Allow Owner to inspect concrete surfaces immediately upon removal of forms.
B. Defective Concrete: Repair and patch defective areas when approved by Owner.
C. Repair or replacement of defective concrete will be determined by the Owner.
D. Do not patch, fill, touch-up, repair or replace exposed concrete except upon express direction of Owner for each individual area.
E. Honeycomb or embedded debris in concrete is not acceptable. Notify owner upon discovery.
3.11 FIELD QUALITY CONTROL
A. Testing and Inspecting: Owner will engage a qualified independent testing and inspecting agency to perform field tests and inspections and prepare test reports.
1. Testing Services: Tests shall be performed according to ACI 301.
END OF SECTION C03300

C05000: STRUCTURAL AND MISCELLANEOUS STEEL

A: STRUCTURAL STEEL

PART 1 - GENERAL

- 1.1 SUMMARY
A. Section includes structural steel and grout.
1.2 DEFINITIONS
A. Structural Steel: Elements of structural-steel frame, as classified by AISC 303, "Code of Standard Practice for Steel Buildings and Bridges."
1. All structural steel work shall conform to the AISC Manual of Steel Construction Thirteenth Edition "Allowable Stress Design."
1.3 PERFORMANCE REQUIREMENTS
A. Connections: Provide details of simple shear connections required by the Contract Documents to be selected or completed by structural-steel fabricator to withstand loads indicated and comply with other information and restrictions indicated.
1. Select and complete connections using schematic details indicated and AISC 360.
2. Use ASD; data are given at service-load level.
B. Moment Connections: Type FR, fully restrained.
1.4 ACTION SUBMITTALS
A. Product Data: For each type of product indicated.
B. Shop Drawings: Show fabrication of structural-steel components.
1. Submit Shop Drawings confirming that the connections have been designed in accordance with the AISC Codes specified. The Shop Drawings shall include complete details and schedules for fabrication and assembly of structural steel members. Reproduction of structural drawings for shop drawings is not permitted.
1.5 INFORMATIONAL SUBMITTALS
A. Qualification Data: For qualified installer, fabricator, and testing agency.
B. Welding certificates.
C. Mill test reports for structural steel, including chemical and physical properties.
D. Source quality-control reports.
1.6 QUALITY ASSURANCE
A. Fabricator Qualifications: A qualified fabricator that participates in the AISC Quality Certification Program and is designated an AISC-Certified Plant, Category STD.
B. Installer Qualifications: 5 years experience with projects of similar complexity.
C. Welding Qualifications: Qualify procedures and personnel according to AWS D1.1D1.1M, "Structural Welding Code - Steel."
D. Comply with applicable provisions of the following specifications and documents:
1. AISC 303.
2. AISC 360.
3. RCSC's "Specification for Structural Joints Using ASTM A 325 or A 490 Bolts."
PART 2 - PRODUCTS (C05120)
2.1 STRUCTURAL-STEEL MATERIALS
A. W-Shapes: ASTM A 992/A 992M.
B. Channels: Angles, M, S-Shapes: ASTM A 36/A 36M.
C. Plate and Bar: ASTM A 36/A 36M.
D. Cold-Formed Hollow Structural Sections: ASTM A 588, Grade B, unless otherwise indicated.
E. Steel Pipe: ASTM A 53/A 53M, Type E, Grade B, unless otherwise indicated.
F. Welding Electrodes: Comply with AWS F 1.
2.2 BOLTS, NUTS, WASHERS, AND ANCHORS
A. High-Strength Bolts, Nuts, and Washers: ASTM A 490, Type 1, heavy-hex steel structural bolts or tension-control, bolt-nut-washer assemblies with spliced ends; ASTM A 563, Grade DH, (ASTM A 563M, Class 105) heavy-hex carbon-steel nuts; and ASTM F 436 (ASTM F 436M), Type 1, hardened carbon-steel washers with plain finish.
1. Direct-Tension Indicators: ASTM F 559, Type 450, compressible-washer type with plain finish.
B. High-Strength Bolts, Nuts, and Washers: ASTM A 490, Type 1, heavy-hex steel structural bolts or tension-control, bolt-nut-washer assemblies with spliced ends; ASTM A 563, Grade DH, (ASTM A 563M, Class 105) heavy-hex carbon-steel nuts; and ASTM F 436 (ASTM F 436M), Type 1, hardened carbon-steel washers with plain finish.
1. Direct-Tension Indicators: ASTM F 559, Type 450, compressible-washer type with plain finish.
C. Headed Anchor Rods: ASTM F 1554, Grade 55, weldable, straight.
1. Finish: Plain.
2. Embed 12 Bolt diameters of 12" minimum.
D. Threaded Rods: ASTM A.
1. Finish: Plain.
2. Embed 12 Bolt diameters or 12" minimum.
2.3 PRIMER
A. Low-Emitting Materials: Paints and coatings shall comply with the testing and product requirements of the California Department of Health Services' "Standard Practice for the Testing of Volatile Organic Emissions from Various Sources Using Small-Scale Environmental Chambers."
B. Primer: SSPC-Part 23, Type II, zinc oxide, alkyl, based oil primer.
C. Primer: Fabricator's standard lead- and chromate-free, nonaesthetic, rust-inhibiting primer complying with MPI 079 and compatible with topcoat.
2.4 GROUT
A. Nonmetallic, Shrinkage-Resistant Grout: ASTM C 1107, factory-packaged, nonmetallic aggregate grout, nonconcrete and nonstaining, mixed with water to consistency suitable for application and a 30-minute working time.
2.5 FABRICATION
A. Structural Steel: Fabricate and assemble in shop to greatest extent possible. Fabricate according to AISC's "Code of Standard Practice for Steel Buildings and Bridges" and AISC 360.
B. Shear Connections: Prepare steel surfaces as recommended by manufacturer of shear connectors. Use automatic arc welding of headed stud shear connectors according to AWS D1.1D1.1M and manufacturer's written instructions (Do not use single fillet plate).
2.6 SHOP CONNECTIONS
A. High-Strength Bolts: Shop install high-strength bolts according to RCSC's "Specification for Structural Joints Using ASTM A 325 or A 490 Bolts" for type of bolt and type of joint specified.
1. Joint Type: Snug tightened.
2. Minimum diameter of bolts shall be 1/2", maximum diameter shall be 1 1/8" unless noted otherwise on drawings.
3. Provide at least 1/2" bolt spacing per connection.
B. Weld Connections: Comply with AWS D1.1D1.1M for tolerances, appearances, welding procedure specifications, weld quality, and methods used in correcting welding work.
2.7 SHOP PRIMING
A. Shop prime all steel surfaces except the following:
1. Surfaces embedded in concrete or mortar. Extend priming of partially embedded members to a depth of 2 inches (50 mm).
2. Surfaces to be field welded.
3. Surfaces to be high-strength bolted with slip-critical connections.
B. Surface Preparation: Clean surfaces to be painted. Remove loose rust and mill scale and spatter, slag, or flux deposits. Prepare surfaces according to the following specifications and standards:
1. SSPC-SP 2, "Hand Tool Cleaning."
2. SSPC-SP 3, "Power Tool Cleaning."
C. Priming: Immediately after surface preparation, apply primer according to manufacturer's written instructions. Field rate recommended by SSPC to provide a minimum dry film thickness of 2.5 mils (0.05 mm). Use priming that results in full coverage of joints, corners, edges, and exposed surfaces.
2.8 SOURCE QUALITY CONTROL
A. Testing Agency: Owner will engage an independent testing and inspecting agency to perform shop tests and inspections and prepare test reports.
1. Provide testing agency with access to places where structural-steel work will be fabricated or produced to perform tests and inspections.
B. Correct deficiencies in Work that test reports and inspections indicate does not comply with the Contract Documents.
C. Bolted Connections: Shop-bolted connections will be tested and inspected according to RCSC's "Specification for Structural Joints Using ASTM A 325 or A 490 Bolts."
D. Welded Connections: In addition to visual inspection, shop-welded connections will be tested and inspected according to AWS D1.1D1.1M and the following inspection procedures, at testing agency's option:
1. Liquid Penetrant Inspection: ASTM E 165.
2. Magnetic Particle Inspection: ASTM E 709, performed on root pass and on finished weld. Cracks or zones of incomplete fusion or penetration will not be accepted.
3. Ultrasonic Inspection: ASTM E 164.
4. Radiographic Inspection: ASTM E 94.
PART 3 - EXECUTION
3.1 EXAMINATION
A. Verify that steel Erector preparations, concrete, masonry-bearing surfaces and locations of anchor rods, bearing plates, and other embedded items, comply with requirements.
Proceed with installation only after all conditions have been corrected.
3.2 CONNECTIONS
A. Fabricate and assemble accurately in locations and elevations indicated and according to AISC 303 and AISC 360.
B. Steel Beaming and Leveling Plates: Clean concrete- and masonry-bearing surfaces of bond-reducing materials, and clean steel surfaces prior to setting plates. Clean bottom surface of plates.
1. Set plates on lateral members on wedges, shims, or setting nuts as required.
2. Field plates shall be set to top of baseplate.
3. Plug-lightning bolts, base plate anchor rods, tension anchor rods in moment frames after supported members have been positioned and plumbed. Do not remove wedges or shims but, if protruding, cut off flush with edge of plate before packing with grout.
4. Temporarily pack grout solidly between bearing surfaces and plates so no voids remain. Neatly finish exposed surfaces.
5. Grout and allow to cure. Comply with manufacturer's written installation instructions for shrinkage-resistant grout.
C. Maintain erection tolerances of structural steel within AISC's "Code of Standard Practice for Steel Buildings and Bridges."
3.3 FIELD CONNECTIONS
A. High-Strength Bolts: Install high-strength bolts according to RCSC's "Specification for Structural Joints Using ASTM A 325 or A 490 Bolts" for type of bolt and type of joint specified.
1. Joint Type: Snug tightened.
B. Weld Connections: Comply with AWS D1.1D1.1M for tolerances, appearances, welding procedure specifications, weld quality, and methods used in correcting welding work.
1. Comply with AISC 303 and AISC 360 for bearing, alignment, adequacy of temporary connections, and removal of joint on surfaces adjacent to field welds.
3.4 FIELD QUALITY CONTROL
A. Testing Agency: Owner will engage a qualified independent testing and inspecting agency to inspect field welds and high-strength bolted connections.
B. Bolted Connections: Bolted connections will be tested and inspected according to RCSC's "Specification for Structural Joints Using ASTM A 325 or A 490 Bolts."
C. Welded Connections: Field welds will be visually inspected according to AWS D1.1D1.1M.
1. In addition to visual inspection, field welds will be tested and inspected according to AWS D1.1D1.1M and the following inspection procedures, at testing agency's option:
a. Liquid Penetrant Inspection: ASTM E 165.
b. Magnetic Particle Inspection: ASTM E 709, performed on root pass and on finished weld. Cracks or zones of incomplete fusion or penetration will not be accepted.
c. Ultrasonic Inspection: ASTM E 164.
d. Radiographic Inspection: ASTM E 94.
Correct deficiencies in Work that test reports and inspections indicate does not comply with the Contract Documents.
END OF SECTION C05000



Chick-fil-A
5200 Buffington Road
Atlanta, Georgia 30349-
2998



BRITT, PETERS
ASSOCIATES
ARCHITECTURE
INTERIOR DESIGN
PROJECT MANAGEMENT
999 WATERSIDE DRIVE
SUITE 2020
NORFOLK, VA 23510
PH 757.965.5710
BPAP 170944



CHICK-FIL-A
SAR South Cobb Drive FSR
3100 South Cobb Dr SE, Smyrna, GA 30080

FSR# 00810

Table with 3 columns: NO., DATE, DESCRIPTION

Table with 2 columns: CONSULTANT PROJECT #, DATE

SHEET
STRUCTURAL
SPECIFICATIONS
SHEET NUMBER
S-901

Order Plans
9/29/2017 8:04:29 PM

WWW.WORKMADLINE.COM

Copyright © 2017 INTERPLAN. REPEATS COPYRIGHT & OTHER RIGHTS RESPECTING THESE DOCUMENTS TO THE ORIGINAL SET OF PAPERS OR MASTER COPY WHICH THEY WERE PREPARED. REPRODUCTIONS, CHANGES OR ADDITIONS ARE PROHIBITED.